

*CLAIM AMENDMENTS*

Claims 1-19. (Canceled)

20. (Currently Amended) A process for forming a pattern of fluorescent substance into the cell of a fluorescent substance display substrate comprising providing inside the cell two separate layers which are (i) a resin composition (A) layer and (ii) a photosensitive resin composition (B) layer, exposing the layers to light, developing the exposed layers, and baking the developed layers; wherein the resin composition (A) layer consists essentially of an acrylic polymer (a) having a weight average molecular weight of 10000 to 300000 and an acid number of 80 to 250 mgKOH/g, a fluorescent substance (b), a compound containing at least one ethylenically unsaturated group (c) having a viscosity of 5-15000 mPa.sec at 20 °C, and 0.1 to 15 parts by weight of a polymerization inhibitor (d) based on 100 parts by weight of the acrylic polymer (a), ~~and~~ the resin composition (A) layer is disposed between the inside of the cell and the photosensitive resin composition (B) layer, and the photosensitive resin composition (B) comprises a photoinitiator.

21. (Currently Amended) A process for forming a pattern of fluorescent substance into the cell of a fluorescent substance display substrate, wherein a resin composition (A) layer, consisting essentially of an acrylic polymer (a) having a weight average molecular weight of 10000 to 300000 and an acid number of 80 to 250 mgKOH/g, a fluorescent substance (b), a compound containing at least one ethylenically unsaturated group (c) having a viscosity of 5-15000 mPa.sec at 20 °C, and 0.1 to 15 parts by weight of a polymerization inhibitor (d) based on 100 parts by weight of the acrylic polymer (a), and a photosensitive resin composition (B) layer are formed inside the cell, and then they are exposed, developed and baked, wherein the photosensitive resin composition (B) layer is formed in the cell after the resin composition (A) layer is formed, and the photosensitive resin composition (B) comprises a photoinitiator.

22. (Currently Amended) A process for forming a pattern of fluorescent substance into the cell of a fluorescent substance display substrate comprising providing inside the cell two separate layers which are (i) a resin composition (A) layer and (ii) a photosensitive resin composition (B) layer, wherein the resin composition (A) layer,

consisting essentially of an acrylic polymer (a) having a weight average molecular weight of 10000 to 300000 and an acid number of 80 to 250 mgKOH/g, a fluorescent substance (b), a compound containing at least one ethylenically unsaturated group (c) having a viscosity of 5-15000 mPa.sec at 20 °C, and 0.1 to 15 parts by weight of a polymerization inhibitor (d) based on 100 parts by weight of an acrylic polymer (a), the photosensitive resin composition (B) comprises a photoinitiator and the photosensitive resin composition (B) layer are formed inside the cell, and then they are exposed, developed and baked, wherein the photosensitive resin composition (B) layer is formed in the cell after the resin composition (A) layer is formed.